TT-E-529G
SEMIGLOSS ALKYD ENAMEL

TECHNICAL DATA SHEET

DESCRIPTION:

TT-P-529G is a semi-gloss, alkyd enamel formulated for interior and exterior metal and wood surfaces. This coating is primarily used as a medium dry finish coat on equipment.

PROPERTIES:

COLORS: full range	Fed Std 595b
GRIND	Not under 6
Specular Gloss	15-25 @ 60 Deg.
Viscosity	67-77 KU
Dry Times @77 °F	To Touch 2hrs. *
	Dry Hard 8 hrs. *
	Full Hard 72 hrs. *

* times will vary with humidity, temperature and film thickness.

Thinner	Xylene
Shelf Life @ 77 °F	12 months (D.M.)

ADVANTAGES:

Interior/Exterior use
Semi-Gloss Finish
Meets TT-E-529G
Fast Production Time

USES:

Steel / Wood
Machinery
Tanks
Towers

SAFETY:

Refer to **Material Safety Data Sheets** before use
FOR PROFFESIONAL USE ONLY
CONTENTS ARE FLAMMABLE
AVOID BREATHING MIST OR VAPOR

PRIMERS

STEEL:	TT-P-664D
ALUMINUM:	MIL-C-8514C (1st)
	MTT-P-664D (2nd)

Distributed by:

PACIFIC RESINS & COATINGS LTD.
AIRCRAFT COATINGS & RESINS
151- 5489 Byrne Road, Burnaby,BC, Canada, V5J 3J1
Phone (604)432-6111 or (604)430-4151
Fax (604)432-7006 e-mail info@pwpaints.com
Web Site: www.pwpaints.com

APPLICATION:

TT-E-529G Enamels can be applied by conventional or airless spray application. For spray application thin up to 10% or as needed with zylene. For brushing use as is or with minimum thinning.